



# MACHINING CONDITIONS

CCMT 060204 NN LT 1000

T0001888

Material Group	SAPPHIRE TOOLS	Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc		
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]	[mm/t]	[m/min]		
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.3	2.1	0.08	0.2	0.37	180	330	1	0.14	300	
				190 HB	0.3	1.8	0.08	0.19	0.32	180	280	1	0.14	260	
				250 HB	0.3	1.8	0.08	0.17	0.3	180	250	1	0.14	240	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.3	1.8	0.08	0.17	0.3	120	250	1	0.11	240	
				280 HB	0.3	1.4	0.08	0.15	0.25	120	210	1	0.1	200	
				180 HB	0.3	1.8	0.08	0.17	0.31	120	280	1	0.11	260	
				350 HB	0.3	1.4	0.08	0.15	0.22	120	180	1	0.1	180	
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.3	1.8	0.07	0.15	0.25	70	190	0.9	0.08	180	
				280 HB	0.3	1.8	0.07	0.14	0.25	70	150	0.9	0.08	140	
				320 HB	0.3	1.4	0.07	0.12	0.2	70	130	0.9	0.08	120	
				350 HB	0.3	1.4	0.07	0.12	0.16	70	110	0.9	0.08	110	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.3	1.8	0.06	0.15	0.2	170	270	1	0.07	260	
				240 HB	0.3	1.8	0.06	0.15	0.16	160	220	1	0.06	210	
	Duplex	5	X2CrNi23-4, S31500	290 HB	0.3	1.4	0.06	0.12	0.12	80	150	0.9	0.06	140	
Cast Iron	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	310 HB	0.3	1.4	0.06	0.12	0.12	70	140	0.9	0.06	140	
	Grey	7	GG20, GG40, EN-GJL-250, N030B	200 HB	0.3	1.8	0.06	0.15	0.2	170	250	0.9	0.07	240	
				42 HRc	0.3	1.4	0.06	0.14	0.16	120	190	0.8	0.06	180	
				150 HB	0.3	2.1	0.06	0.17	0.4	170	250	1	0.14	240	
NiTi Alloy	Malleable & Nodular	8	GGG40, GGG70, 50005	200 HB	0.3	2.1	0.06	0.17	0.37	160	230	1	0.14	220	
				250 HB	0.3	2.1	0.06	0.17	0.37	150	210	1	0.14	200	
				150 HB	0.3	1.8	0.06	0.15	0.3	120	250	1	0.1	240	
	Fe, Ni & Co Based	9	Incoloy 800	200 HB	0.3	1.8	0.06	0.15	0.25	120	230	1	0.1	220	
				250 HB	0.3	1.4	0.07	0.13	0.16	30	50	0.7	0.08	40	
Hardened Materials	Stellite 21	10	Stellite 21	350 HB	0.3	1.4	0.07	0.13	0.16	20	50	0.7	0.08	35	
				T40	-	0.3	1.4	0.07	0.12	0.16	40	60	0.7	0.08	50
				TiAl6V4	-	0.3	1.4	0.07	0.14	0.2	50	70	0.7	0.11	60
	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.3	1	0.04	0.08	0.08	30	50	0.5	0.05	40	
				Ni-Hard 2	400 HB	0.3	1.1	0.04	0.1	0.11	40	60	0.6	0.08	50
				45 HRc	0.3	1.3	0.04	0.1	0.12	50	100	0.7	0.08	90	
Aluminium	AI (>8%Si)	12	AlSi12	50 HRc	0.3	1.1	0.04	0.09	0.11	40	90	0.6	0.06	80	
				55 HRc	0	1	0.04	0.08	0.08	40	80	0.5	0.05	70	
				130 HB	0.3	2.8	0.08	0.26	0.43	200	400	1	0.18	350	