




MACHINING CONDITIONS

CNGG 120404 NS LT 1110S

T0004579

Material Group		Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]	[mm/t]	[m/min]	
NITi Alloy	Ti Based	10	T40	-	0.3	2	0.06	0.16	0.22	50	70	1.5	0.13	60
			TiAl6V4	-	0.3	2	0.06	0.14	0.2	40	60	1.5	0.11	50