



MACHINING CONDITIONS

SCMT 09T304 NN LT 10

FT001459

	Material Group	SAPPHIRE CUTTING TOOLS Group	Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc
					min[mm]	max[mm]	min[mm/t]	max[mm/t]	[mm^2]	min[m/min]	max [m/min]	[mm]	[mm/t]	[m/min]
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.3	4	0.11	0.26	0.72	180	330	2.5	0.18	300
				190 HB	0.3	3.3	0.11	0.25	0.62	180	280	2.5	0.18	260
				250 HB	0.3	3.3	0.11	0.23	0.58	180	250	2.5	0.18	240
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.3	3.3	0.1	0.23	0.58	120	250	2.5	0.14	240
				280 HB	0.3	2.7	0.1	0.21	0.48	120	210	2.5	0.13	200
				180 HB	0.3	3.3	0.1	0.23	0.6	120	280	2.5	0.14	260
				350 HB	0.3	2.7	0.1	0.21	0.43	120	180	2.5	0.13	180
	High Alloyed	3	X40CrMOV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.3	3.3	0.09	0.21	0.48	70	190	2.1	0.1	180
				280 HB	0.3	3.3	0.09	0.18	0.48	70	150	2.1	0.1	140
				320 HB	0.3	2.7	0.09	0.16	0.38	70	130	2.1	0.1	120
				350 HB	0.3	2.7	0.09	0.16	0.31	70	110	2.1	0.1	110
	Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.3	3.3	0.08	0.21	0.38	170	270	2.5	0.09
240 HB					0.3	3.3	0.08	0.21	0.31	160	220	2.5	0.08	210
Duplex		5	X2CrNiN23-4, S31500	290 HB	0.3	2.7	0.08	0.16	0.24	80	150	2.1	0.08	140
				310 HB	0.3	2.7	0.08	0.16	0.24	70	140	2.1	0.08	140
Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.3	3.3	0.08	0.21	0.38	170	250	2.1	0.09	240	
			42 HRc	0.3	2.7	0.08	0.18	0.31	120	190	1.9	0.08	180	
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.3	4	0.08	0.23	0.77	170	250	2.5	0.18	240
				200 HB	0.3	4	0.08	0.23	0.72	160	230	2.5	0.18	220
				250 HB	0.3	4	0.08	0.23	0.72	150	210	2.5	0.18	200
Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.3	3.3	0.08	0.21	0.58	120	250	2.5	0.13	240	
			200 HB	0.3	3.3	0.08	0.21	0.48	120	230	2.5	0.13	220	
			250 HB	0.3	3.3	0.08	0.21	0.48	120	190	2.5	0.13	180	
NiTi Alloy	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.3	2.7	0.09	0.17	0.31	30	50	1.6	0.1	40
			Inconel 700	250 HB	0.3	2.7	0.09	0.17	0.31	30	50	1.6	0.1	40
			Stellite 21	350 HB	0.3	2.7	0.09	0.17	0.31	20	50	1.6	0.1	35
Ti Based	10	T40	-	0.3	2.7	0.09	0.16	0.31	40	60	1.6	0.1	50	
		TiAl6V4	-	0.3	2.7	0.09	0.18	0.38	50	70	1.6	0.14	60	
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.3	1.9	0.05	0.1	0.16	30	50	1.1	0.06	40
			Ni-Hard 2	400 HB	0.3	2.1	0.05	0.14	0.2	40	60	1.4	0.1	50
			X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.3	2.4	0.05	0.14	0.24	50	100	1.8	0.1	90
				50 HRc	0.3	2	0.05	0.12	0.2	40	90	1.4	0.08	80
				55 HRc	0.3	1.9	0.05	0.1	0.16	40	80	1.1	0.06	70
Aluminium	Al (>8%Si)	12	AlSi12	130 HB	0.3	5.3	0.1	0.35	0.84	200	400	2.5	0.23	350