

Material Group	SAPPHIRE CUTTING TOOLS Group	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	min [m/min]	max [m/min]			
Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	7	0.18	0.46	190	330	3	0.34	250
			190 HB	0.5	7	0.18	0.46	190	300	3	0.34	220
			250 HB	0.5	7	0.18	0.46	190	250	3	0.34	200
Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	7	0.15	0.36	150	210	3	0.3	180
			280 HB	0.5	7	0.15	0.32	130	190	3	0.27	150
			180 HB	0.5	7	0.15	0.36	150	240	3	0.3	200
			350 HB	0.5	7	0.15	0.32	130	170	3	0.27	140
High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	5	0.12	0.32	90	150	2.3	0.27	130
			280 HB	0.5	5	0.12	0.32	90	130	2.3	0.27	120
			320 HB	0.5	5	0.12	0.26	60	110	2.3	0.24	100
			350 HB	0.5	5	0.12	0.26	60	90	2.3	0.24	80
Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.5	7	0.15	0.32	190	250	3	0.27	220
			240 HB	0.5	7	0.12	0.29	160	210	3	0.27	190
Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	5	0.12	0.26	70	130	2.3	0.24	100
			310 HB	0.5	5	0.12	0.26	70	120	2.3	0.24	90
Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	7	0.15	0.32	150	210	3	0.27	190
			42 HRc	0.5	5	0.15	0.26	90	150	2.3	0.24	130
Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	7	0.18	0.46	150	240	3	0.34	200
			200 HB	0.5	7	0.18	0.46	150	220	3	0.34	180
			250 HB	0.5	7	0.18	0.46	150	190	3	0.34	160
Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	7	0.15	0.41	100	200	3	0.3	180
			200 HB	0.5	7	0.15	0.41	100	180	3	0.3	150
			250 HB	0.5	7	0.15	0.41	100	150	3	0.3	130
Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.5	5	0.12	0.26	30	50	2.3	0.24	32
		Inconel 700	250 HB	0.5	5	0.12	0.26	30	50	2.3	0.24	30
		Stellite 21	350 HB	0.5	5	0.12	0.26	30	50	2.3	0.24	30
Ti Based	10	T40	-	0.5	5	0.12	0.26	30	60	2.3	0.24	40
		TiAl6V4	-	0.5	5	0.12	0.29	40	70	2.3	0.27	55
Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.5	1.5	0.1	0.2	30	60	0.8	0.18	40
		Ni-Hard 2	400 HB	0.5	2	0.1	0.26	40	80	1.1	0.21	50
		X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.5	2.5	0.1	0.26	40	80	1.5	0.21	60
			50 HRc	0.5	1.8	0.1	0.23	40	70	1.1	0.19	55
			55 HRc	0.5	1.5	0.1	0.2	40	60	0.8	0.18	50
Al (>8%Si)	12	AlSi12	130 HB	0.5	7	0.18	0.46	200	400	3	0.37	280