

| Material Group | SAPPHIRE CUTTING TOOLS Group | Material Example | Hardness | D.O.C | | Feed | | Vc | | Advised D.O.C [mm] | Advised Feed [mm/t] | Advised Vc [m/min] | |
|------------------------|---|------------------------------------|---|----------------------|---------|-----------|------------|-------------|-------------|-----------------------|------------------------|-----------------------|------|
| | | | | min[mm] | max[mm] | min[mm/t] | max [mm/t] | min [m/min] | max [m/min] | | | | |
| Steel | Non Alloyed | C35, Ck45, 1020, 1045, 1060, 28Mn6 | 125 HB | 0.5 | 7 | 0.18 | 0.46 | 190 | 330 | 3 | 0.34 | 250 | |
| | | | 190 HB | 0.5 | 7 | 0.18 | 0.46 | 190 | 300 | 3 | 0.34 | 220 | |
| | | | 250 HB | 0.5 | 7 | 0.18 | 0.46 | 190 | 250 | 3 | 0.34 | 200 | |
| | Low Alloyed | 2 | 42CrMo4, St50, Ck60, 4140, 4340, 100Cr6 | 230 HB | 0.5 | 7 | 0.15 | 0.36 | 150 | 210 | 3 | 0.3 | 180 |
| | | | | 280 HB | 0.5 | 7 | 0.15 | 0.32 | 130 | 190 | 3 | 0.27 | 150 |
| | | | | 180 HB | 0.5 | 7 | 0.15 | 0.36 | 150 | 240 | 3 | 0.3 | 200 |
| | | | | 350 HB | 0.5 | 7 | 0.15 | 0.32 | 130 | 170 | 3 | 0.27 | 140 |
| | High Alloyed | 3 | X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19 | 220 HB | 0.5 | 5 | 0.12 | 0.32 | 90 | 150 | 2.3 | 0.27 | 130 |
| | | | | 280 HB | 0.5 | 5 | 0.12 | 0.32 | 90 | 130 | 2.3 | 0.27 | 120 |
| | | | | 320 HB | 0.5 | 5 | 0.12 | 0.26 | 60 | 110 | 2.3 | 0.24 | 100 |
| | | | | 350 HB | 0.5 | 5 | 0.12 | 0.26 | 60 | 90 | 2.3 | 0.24 | 80 |
| | Stainless Steel | Austenitic | 4 | 304, 316, X5CrNi18-9 | 180 HB | 0.5 | 7 | 0.15 | 0.32 | 190 | 250 | 3 | 0.27 |
| 240 HB | | | | | 0.5 | 7 | 0.12 | 0.29 | 160 | 210 | 3 | 0.27 | 190 |
| Duplex | | 5 | X2CrNiN23-4, S31500 | 290 HB | 0.5 | 5 | 0.12 | 0.26 | 70 | 130 | 2.3 | 0.24 | 100 |
| | | | | 310 HB | 0.5 | 5 | 0.12 | 0.26 | 70 | 120 | 2.3 | 0.24 | 90 |
| Ferritic & Martensitic | | 6 | 410, X6Cr17, 17-4 PH, 430 | 200 HB | 0.5 | 7 | 0.15 | 0.32 | 150 | 210 | 3 | 0.27 | 190 |
| | | | | 42 HRc | 0.5 | 5 | 0.15 | 0.26 | 90 | 150 | 2.3 | 0.24 | 130 |
| Cast Iron | Grey | 7 | GG20, GG40, EN-GJL-250, N030B | 150 HB | 0.5 | 7 | 0.18 | 0.46 | 150 | 240 | 3 | 0.34 | 200 |
| | | | | 200 HB | 0.5 | 7 | 0.18 | 0.46 | 150 | 220 | 3 | 0.34 | 180 |
| | | | | 250 HB | 0.5 | 7 | 0.18 | 0.46 | 150 | 190 | 3 | 0.34 | 160 |
| | Malleable & Nodular | 8 | GGG40, GGG70, 50005 | 150 HB | 0.5 | 7 | 0.15 | 0.41 | 100 | 200 | 3 | 0.3 | 180 |
| | | | | 200 HB | 0.5 | 7 | 0.15 | 0.41 | 100 | 180 | 3 | 0.3 | 150 |
| | | | | 250 HB | 0.5 | 7 | 0.15 | 0.41 | 100 | 150 | 3 | 0.3 | 130 |
| NITI Alloy | Fe, Ni & Co Based | 9 | Incoloy 800 | 240 HB | 0.5 | 5 | 0.12 | 0.26 | 30 | 50 | 2.3 | 0.24 | 32 |
| | | | Inconel 700 | 250 HB | 0.5 | 5 | 0.12 | 0.26 | 30 | 50 | 2.3 | 0.24 | 30 |
| | | | Stellite 21 | 350 HB | 0.5 | 5 | 0.12 | 0.26 | 30 | 50 | 2.3 | 0.24 | 30 |
| | Ti Based | 10 | T40 | - | 0.5 | 5 | 0.12 | 0.26 | 30 | 60 | 2.3 | 0.24 | 40 |
| TiAl6V4 | | | - | 0.5 | 5 | 0.12 | 0.29 | 40 | 70 | 2.3 | 0.27 | 55 | |
| Hardened Materials | Steel Chilled Cast Iron White Cast Iron | 11 | G-X300CrMo15 | 55 HRc | 0.5 | 1.5 | 0.1 | 0.2 | 30 | 60 | 0.8 | 0.18 | 40 |
| | | | Ni-Hard 2 | 400 HB | 0.5 | 2 | 0.1 | 0.26 | 40 | 80 | 1.1 | 0.21 | 50 |
| | | | X100CrMo13, 440C, G-X260NiCr42 | 45 HRc | 0.5 | 2.5 | 0.1 | 0.26 | 40 | 80 | 1.5 | 0.21 | 60 |
| | | | | 50 HRc | 0.5 | 1.8 | 0.1 | 0.23 | 40 | 70 | 1.1 | 0.19 | 55 |
| | | | | 55 HRc | 0.5 | 1.5 | 0.1 | 0.2 | 40 | 60 | 0.8 | 0.18 | 50 |
| Aluminium | Al (>8%Si) | 12 | AlSi12 | 130 HB | 0.5 | 7 | 0.18 | 0.46 | 200 | 400 | 3 | 0.37 | 280 |