




MACHINING CONDITIONS

SNMG 120408 NX LT 1110S

T0004698

Material Group	 Group	Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm ²]	min [m/min]	max [m/min]	[mm]	[mm/t]	[m/min]	
NITTI Alloy	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.5	3	0.25	0.49	0.94	30	50	2	0.38	30
			Inconel 700	250 HB	0.5	3	0.25	0.49	0.94	30	50	2	0.38	30
			Stellite 21	350 HB	0.5	3	0.25	0.49	0.94	30	40	2	0.38	30
	Ti Based	10	T40	-	0.5	3	0.25	0.49	0.94	40	60	2	0.41	45
			TiAl6V4	-	0.5	3.5	0.25	0.56	1.07	50	70	2	0.45	55