



MACHINING CONDITIONS

TNMG 220408 NX LT 1000

T0003013

Material Group	SAPPHIRE CUTTING TOOLS Group	Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc		
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]	[mm/t]	[m/min]		
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	7	0.18	0.5	1.71	180	330	3	0.36	240	
				190 HB	0.5	7	0.18	0.5	1.71	180	280	3	0.33	220	
				250 HB	0.5	7	0.18	0.45	1.43	180	250	3	0.31	200	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	5.6	0.18	0.45	1.14	120	250	3	0.3	180	
				280 HB	0.5	5.6	0.16	0.4	1.14	120	210	3	0.29	150	
				180 HB	0.5	7	0.18	0.45	1.14	120	280	3	0.3	200	
				350 HB	0.5	4.9	0.16	0.4	0.95	120	180	2.7	0.29	130	
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	5.6	0.16	0.4	1.14	70	190	2.5	0.29	140	
				280 HB	0.5	5.6	0.16	0.4	1.14	70	150	2.5	0.29	120	
				320 HB	0.5	4.2	0.16	0.35	0.76	70	130	2.2	0.27	100	
				350 HB	0.5	4.2	0.16	0.35	0.76	70	110	2.2	0.27	90	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.5	7	0.18	0.4	1.14	170	270	3	0.24	190	
				240 HB	0.5	7	0.18	0.4	0.95	160	220	3	0.21	170	
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	5.6	0.16	0.35	0.76	80	150	2.5	0.23	100	
				310 HB	0.5	5.6	0.16	0.35	0.76	70	140	2.5	0.23	90	
Cast Iron	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	7	0.16	0.4	0.67	170	250	2.5	0.19	190	
				42 HRc	0.5	5.6	0.16	0.4	0.67	120	190	2.2	0.19	130	
				150 HB	0.5	7	0.13	0.6	1.9	170	250	3	0.33	200	
	Grey	7	GG20, GG40, EN-GJL-250, N030B	200 HB	0.5	7	0.13	0.6	1.71	160	230	3	0.33	180	
Cast Iron	Malleable & Nodular	8		250 HB	0.5	7	0.13	0.55	1.71	150	210	3	0.33	160	
				150 HB	0.5	7	0.13	0.5	1.43	120	250	3	0.29	180	
				200 HB	0.5	7	0.13	0.5	1.24	120	230	3	0.29	160	
NiTi Alloy	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.5	4.2	0.18	0.35	0.67	30	50	2	0.27	30	
				250 HB	0.5	4.2	0.18	0.35	0.67	30	50	2	0.27	30	
				350 HB	0.5	4.2	0.18	0.35	0.67	30	40	2	0.27	30	
	Ti Based	10	T40	-	0.5	4.2	0.18	0.35	0.67	40	60	2	0.29	45	
Hardened Materials			TiAl6V4	-	0.5	4.9	0.18	0.4	0.76	50	70	2	0.31	55	
Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.5	2.1	0.1	0.2	0.29	30	50	1	0.14	40		
		Ni-Hard 2	400 HB	0.5	2.8	0.1	0.25	0.38	40	60	1.5	0.17	50		
		X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.5	3.5	0.1	0.3	0.57	50	100	2	0.24	80		
Aluminium	AI (>8%Si)	12	AlSi12	130 HB	0.5	8.4	0.18	0.6	1.71	200	400	3	0.38	280	