

Material Group	SAPPHIRE CUTTING TOOLS Group	Material Example	Hardness	D.O.C		Feed		Amax [mm <sup>2</sup> ]	Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]		min [m/min]	max [m/min]				
Steel	Non Alloyed	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.3	3	0.11	0.23	0.6	180	330	2	0.18	300	
			190 HB	0.3	2.5	0.11	0.22	0.52	180	280	2	0.18	260	
			250 HB	0.3	2.5	0.11	0.2	0.48	180	250	2	0.18	240	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.3	2.5	0.1	0.2	0.48	120	250	2	0.14	240
				280 HB	0.3	2	0.1	0.18	0.4	120	210	2	0.13	200
				180 HB	0.3	2.5	0.1	0.2	0.5	120	280	2	0.14	260
				350 HB	0.3	2	0.1	0.18	0.36	120	180	2	0.13	180
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.3	2.5	0.09	0.18	0.4	70	190	1.7	0.1	180
				280 HB	0.3	2.5	0.09	0.16	0.4	70	150	1.7	0.1	140
				320 HB	0.3	2	0.09	0.14	0.32	70	130	1.7	0.1	120
				350 HB	0.3	2	0.09	0.14	0.26	70	110	1.7	0.1	110
	Stainless Steel	Austenitic	304, 316, X5CrNi18-9	180 HB	0.3	2.5	0.08	0.18	0.32	170	270	2	0.09	260
240 HB				0.3	2.5	0.08	0.18	0.26	160	220	2	0.08	210	
Duplex		X2CrNiN23-4, S31500	290 HB	0.3	2	0.08	0.14	0.2	80	150	1.7	0.08	140	
			310 HB	0.3	2	0.08	0.14	0.2	70	140	1.7	0.08	140	
Ferritic & Martensitic		6	410, X6Cr17, 17-4 PH, 430	200 HB	0.3	2.5	0.08	0.18	0.32	170	250	1.7	0.09	240
				42 HRc	0.3	2	0.08	0.16	0.26	120	190	1.5	0.08	180
Cast Iron	Grey	GG20, GG40, EN-GJL-250, N030B	150 HB	0.3	3	0.08	0.2	0.64	170	250	2	0.18	240	
			200 HB	0.3	3	0.08	0.2	0.6	160	230	2	0.18	220	
			250 HB	0.3	3	0.08	0.2	0.6	150	210	2	0.18	200	
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.3	2.5	0.08	0.18	0.48	120	250	2	0.13	240
				200 HB	0.3	2.5	0.08	0.18	0.4	120	230	2	0.13	220
				250 HB	0.3	2.5	0.08	0.18	0.4	120	190	2	0.13	180
NITI Alloy	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.3	2	0.09	0.15	0.26	30	50	1.3	0.1	40
			Inconel 700	250 HB	0.3	2	0.09	0.15	0.26	30	50	1.3	0.1	40
			Stellite 21	350 HB	0.3	2	0.09	0.15	0.26	20	50	1.3	0.1	35
	Ti Based	10	T40	-	0.3	2	0.09	0.14	0.26	40	60	1.3	0.1	50
TiAl6V4			-	0.3	2	0.09	0.16	0.32	50	70	1.3	0.14	60	
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	11	G- X300CrMo15	55 HRc	0.3	1.4	0.05	0.09	0.13	30	50	0.9	0.06	40
			Ni-Hard 2	400 HB	0.3	1.6	0.05	0.12	0.17	40	60	1.1	0.1	50
			X100CrMo13, 440C, G- X260NiCr42	45 HRc	0.3	1.8	0.05	0.12	0.2	50	100	1.4	0.1	90
				50 HRc	0.3	1.5	0.05	0.1	0.17	40	90	1.1	0.08	80
				55 HRc	0.3	1.4	0.05	0.09	0.13	40	80	0.9	0.06	70
Aluminium	Al (>8%Si)	12	AlSi12	130 HB	0.3	4	0.1	0.3	0.7	200	400	2	0.23	350